

TECHNICAL DATA SHEET

BUTYLINE

Polymer	Bromo-butyl	
Colour	Black with CN bonding layer	
Specific Gravity	1.27 g/cm³	ASTM D297
Hardness	50° ± 5° Shore A	ASTM D2240
Abrasion	300mm³ (max) @ 10N	ASTM D5963
Tensile Strength	5 MPa (min)	ASTM D412
Elongation @ break	370 % (min)	ASTM D412
Tear Strength	15 N/mm (min)	ASTM D624
Temperature Range	-25°C to +90°C	

