

TECHNICAL DATA SHEET

EPDM POTABLE WATER

Polymer	EPDM	
Standards	Meets the requirements of; AS/NZS 4020 : 2005 AS 1646.2 : 2000	
Colour	Black	
Specific Gravity	1.15 g/cm³	ASTM D297
Hardness	70° ± 5° Shore A	ASTM D2240
Abrasion	275mm³ (max) @ 10N	ASTM D5963
Tensile Strength	11 MPa (min)	ASTM D412
Elongation @ break	350 % (min)	ASTM D412
Tear Strength	45 N/mm (min)	ASTM D624
Temperature Range	-30°C to +110°C	

