

TECHNICAL DATA SHEET

F.R.A.S. SKIRTING

Polymer	CR	
Colour	Black	
Specific Gravity	1.40 g/cm³	ASTM D297
Hardness	65° ± 5° Shore A	ASTM D2240
Tensile Strength	12 MPa (min)	ASTM D412
Elongation @ break	300 % (min)	ASTM D412
Temperature Range	-25°C to +90°C	
Flame Test	Test Piece: 6 x 12.5mm x 150mm Flame temp: 900°C Duration: 60 secs Extinguishing Time: 15 secs (max) 7.5 secs (average)	
Electrical Resistance	300 x 10⁶ Ω (max)	

